



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

AC - 5

Tests

Specifications

	Min.	Max.
Viscosity @ 60° C (140° F), Pa s (Poise).....	40 (400).....	60 (600)
Viscosity, @ 135° C (275° F), mm ² / s (Kinematic)		
Table 1.....	110	
Table 2.....	175	
Penetration @ 25° C (77° F), dmm		
Table 1.....	120	
Table 2.....	140	
Flash Point, COC.....	177° C (350° F)	
Solubility in Trichloroethylene, %.....	99.0	

Tests on RTFO Aged Residue

Viscosity @ 60° C (140° F), Pa s (Poise).....	200 (2000)
Ductility @ 25° C(77° F), cm.....	100

Meets or Exceeds:
AASHTO M226-80 (86) Table 1
AASHTO M226-80 (86) Table 2