



U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (253) 383-1651

PG 52 - 28

	Minimum	Maximum
Flash Point, COC, °C	230	
Viscosity @ 135°C, Pa·s		3.0
Dynamic Shear @ 52°C, G*/sin , kPa	1.00	
After RTFO		
Dynamic Shear @ 52°C, G*/sin , kPa	2.20	
Mass Loss, %		1.00
After PAV @ 90°C		
Dynamic Shear @ 16°C, G*·sin , kPa		5000
Creep Stiffness @ -18°C, S, MPa		300
Creep Stiffness @ -18°C, M-value	0.300	