

U. S. Oil & Refining Co.

3001 Marshall Avenue, Tacoma, Washington, 98421 (206) 383-1651



PG 58 - 28

| | Minimum | Maximum |
|------------------------------------|---------|---------|
| Flash Point, COC, °C | 230 | |
| Viscosity @ 135°C, Pa·s | | 3.0 |
| Dynamic Shear @ 58°C, G*/sin , kPa | 1.00 | |
| After RTFO | | |
| Dynamic Shear @ 58°C, G*/sin , kPa | 2.20 | |
| Mass Loss, % | | 1.00 |
| After PAV @ 100°C | | |
| Dynamic Shear @ 19°C, G*·sin , kPa | | 5000 |
| Creep Stiffness @ -18°C, S, MPa | | 300 |
| Creep Stiffness @ -18°C, M-value | 0.300 | |