

U.S. OIL & REFINING CO.
Tacoma, Washington

PAVING ASPHALT
AC-2.5

PAVING GRADE ASPHALT, AC-2.5

Description:

AC-2.5 is an asphalt cement grade which is specified by the original viscosity @60°C (140°F) Poise for use in pavement construction.

This unmodified asphalt is generally used in Alaska.

The AC-2.5 that U.S. Oil produces does meet table I or II of the American Association of State Highway and Transportation Officials (AASHTO) for viscosity grade asphalts.

Storage /Handling:

Personnel must be trained in the proper handling of AC-2.5 and provided the information contained in the Material Safety Data Sheet (MSDS).

The preferred storage temperatures for AC-2.5 is 135°C to 163°C (275°F to 325°F). Unnecessarily high temperatures result in increased hardening and heating costs. These temperatures should be verified with your asphalt supplier.

This asphalt must be stored in insulated tanks, which have hot oil, electric or high-pressure steam heating systems. We recommend that inspection of asphalt storage tanks be done on a regular basis to prevent potential performance problems.

Because of the high temperatures of paving asphalts, extreme care must be exercised in handling them to prevent severe burns. Proper clothing must be worn with face shields, hard hats, long sleeve shirts, pants, boots and rubber-faced insulated gloves being required for protection.

When loading trucks and trailers or transferring paving asphalts into empty tanks care must be taken to prevent boiling-over due to the presence of water. If trucks or trailers have previously hauled a water-based product such as emulsified asphalt, they must be inspected for moisture and may require drying out before loading. Also, hoses and fittings must be inspected regularly for defects.

Usage:

AC-2.5 is a paving asphalt cement primarily used for production of Hot Mix Asphalt (HMA). This product could also be used for sealing the edges of pavement and for crack sealing.

Mixing:

The use of proper mixing temperatures for an AC asphalt like AC-2.5 is not only important to achieving adequate asphalt coating and mix compaction, but also to the asphalt hardening and pavement properties. Therefore, it is important to consider the mixing temperatures recommended in the mix design or by the asphalt supplier

Additional Information:

For additional information on AC-2.5, contact the Asphalt Division of U.S. Oil & Refining Co., 3001 Marshall Avenue, Tacoma, Washington, 98421, Telephone: 253-383-1651 and Fax: 253-572-1717

Disclaimer of Implied Warranties:

U.S. Oil & Refining Co. makes no warranty that the asphalt material discussed in this product bulletin is merchantable or fit for any particular purpose, and there are no warranties, expressed or implied, which extend beyond this product bulletin.

Disclaimer of Expressed Warranties:

Any affirmation of fact or promise contained in this product bulletin shall not be deemed to create an expressed warranty that the asphalt described shall conform to the affirmation or promise. Any description of the asphalt is for the sole purpose of identification and shall not be deemed to create an expressed warranty that the asphalt shall conform to the description. Any sample or model is for illustrative purpose only and shall not be deemed to create an expressed warranty that the whole of the goods shall conform to the sample or model. No affirmation, promise, description, sample or model shall be deemed part of the basis of the bargain of any sale with U.S. Oil & Refining Co.